



Geetha Krishna Spinning Mills Private Limited,

Post Box No. 76, Madurai Road, RAJAPALAYAM - 626 117.

V.K. Subramania Raja

Managing Director

Date : _____

40S COMBED COMPACT WEAVING YARN
TENTATIVE TEST REPORT

Average Count	40.24
CV % for Count	1.45%
Average Lea Strength(lbs)	79.2
CV % for Strength	4.25%
Corrected CSP	3190
Average TPI	27.02
Uster U%	9.53
Thin Places / Km	1
Thick Places / Km	24
Neps / Km	35
Total Imperfections / Km	60
Hairiness (UT-5)	3.56
Hairiness (Sh) (UT-5)	0.87
Single Yarn Strength in Gms	295
RKM (UT J4)	20.5
C.V.% for RKM	7.51
Elongation %	5.34
C.V.% for Elongation	8.37

Ph : 222249, 222278, Fax ; 04563-230867 E-mail: geethakrishna03@sancharnet.in, geethakrishna03@bsnl.in

TIN No. : 33846061014 C.S.T. No. : 512980 dt. 09.02.93 Web:www.geethakrishna.com