



*Geetha Krishna Spinning Mills Private Limited,*

Post Box No. 76, Madurai Road, RAJAPALAYAM - 626 117.

*V.K. Subramania Raja*  
Managing Director

Date: \_\_\_\_\_

### **50's Combed Cone Yarn Test Report**

	50/1s Combed Cone
Average Count	50.30
CV% for Count	1.51
Avg. Lea Strength (lbs)	57.17
CV% for Strength	4.16
Average C.S.P	2875
Uster U%	10.48
Thin Places /Km	5
Thick Places / Km	41
Neps/ Km	80
Total Imperfections/Km	126